

DURA-TRIM[®] 1933HP

- Description:* **DURA-TRIM[®] 1933HP** utilizes a woven fiberglass as the reinforcement for a new high temperature flame resistant flexible polymer coating. This combination of materials enables **DURA-TRIM[®] 1933HP** to achieve excellent dimensional stability, flame resistance, and a high strength to weight ratio.
- Applications:* **DURA-TRIM[®] 1933HP** is used for aircraft insulation blankets, sound attenuation blankets and headliners. It may be tested for any applications requiring a high level of fire protection.
- Available Colors:* **DURA-TRIM[®] 1933HP** is typically dark gray.
- Compliance:* **DURA-TRIM[®] 1933HP** is tested in the Radiant Panel Test Chamber which conforms to 14 CFR Part 25 Appendix F Part VI.

Typical Physical Properties

Weight (oz/yd ²)	4.5
Flame Propagation FAR 25.856 (a) (inches)	< 1
After Flame (seconds)	0
Grab Tensile – (Lbs.)	>120
Standard Roll Width (inches)	54

The information contained in this technical data bulletin is believed to be true and accurate. The data is from historical testing and should not be considered a specification. This information is to be used only as a guide. It is the responsibility of the end user to determine the suitability of our products for each specific application.

RO
Rev 10/24/10
FP