

DURASONIC® 5003

Description: DURASONIC® 5003 is a 0.14 lb/ft² reinforced mass-loaded vinyl barrier.

DURASONIC® is a field proven family of noise-abatement products characterized

by high weight to volume (mass) flexible vinyl structure and meets the

requirements of BMS8-47F Type 4.

Available Colors: Gray.

PHYSICAL PROPERTIES

Test and Methods	<u>Imperial</u>			<u>Metric</u>	
	Spec.	*Typical	Unit	*Typical	Unit
Weight FSTM191.5041	20 ± 2	20 ± 1	oz/yd²	0.68 ± 0.034	kg/m²
Thickness FSTM191.5030	0.018 Max.	0.015 ± 0.003	inches	0.38 ± 0.076	mm
Adhesion ASTM D751	3.0 Min.	10.0 ± 1.0	lbs/inch	44.48 ± 4.4	N/25mm
Vertical Flame (MD/CD) FAR 25.853(a)(1)(ii)					
After Flame	< 15	0.2 / 0.2	seconds	0.2 / 0.2	seconds
Burn Length	< 8	2.7 / 2.6	inches	68.58 / 66.04	mm
Drip Time	< 5	0.0 / 0.0	seconds	0.0 / 0.0	seconds
Grab Tensile (MD/CD) FSTM191.5100	110 Min.	330 / 330 ± 50	lbs	1467.9 / 1467.9 ± 222.4	N
Trap Tear (MD/CD) ASTM D1117	12 Min.	25 / 20 ± 5	lbs	111.2 / 89.0 ± 22.2	N
High Temperature Resistance Section 8.5	Pass	Pass	Pass/Fail	Pass	Pass/Fail
Corrosion Section 8.3	Pass	Pass	Pass/Fail	Pass	Pass/Fail
Standard Width		48	inches	1219.2	mm

^{*}The information contained in this technical data bulletin is believed to be true and accurate. The typical physical properties are from historical testing and should not be considered a specification. This information is to be used only as a guide. It is the responsibility of the end user to determine the suitability of our products for each specific application.

03.01.17 JB