

## **DURATRIM® 3209**

Description: DURATRIM® 3209 utilizes woven fiberglass as the reinforcement for the flexible

PVC covering. The fiberglass makes the material extremely flame resistant, features very high tensile strength for its weight as has superior dimensional

stability.

Applications: Industrial Pipe Wrap, Flexible Ducting, Quilted Sound Blankets, Quilted Aircraft

Insulation, Headlining, Decorative Trim and Divider Curtains.

Available Colors: Duracote's® custom color laboratory can custom match virtually any color. Please

provide a Federal Color Standard 5-digit number, Duracote® color number or a

color swatch.

Compliance: DURATRIM® 3209 is manufactured to meet military specification MIL-C-22787D

Type 1.

## PHYSICAL PROPERTIES

| Test and Methods                       | <u>Imperial</u> |                                  |         | <u>Metric</u>       |         |
|--|-----------------|----------------------------------|---------|---------------------|---------|
|  | Spec.           | *Typical                         | Unit    | *Typical            | Unit    |
| Weight<br>FSTM191.5041                 | 5.8 Min.        | 8.0 ± 0.5                        | oz/yd²  | 0.27 ± 0.017        | kg/m²   |
| Thickness<br>FSTM191.5030              |                 | 0.008 ± 0.0007                   | inches  | 0.2 ± 0.018         | mm      |
| Vertical Flame (MD/CD)<br>FSTM191.5903 |                 |                                  |         |                     |         |
| After Flame                            | < 2             | 0.0 / 0.0                        | seconds | 0.0 / 0.0           | seconds |
| Glow Time                              | < 3             | $1.0 / 1.0 \pm 0.5$              | seconds | $1.0 / 1.0 \pm 0.5$ | seconds |
| Char Length                            | < 2.3           | $1.0 / 1.0 \pm 0.5$              | inches  | 25.4 / 25.4 ± 12.7  | mm      |
| Tensile – Grab (MD/CD)<br>FSTM191.5100 | 110 / 100 Min.  | 260 / 197<br>± 50                | lbs     | 1157 / 876<br>± 222 | N       |
| Tear - Trapezoid (MD/CD)<br>ASTM D1117 | 6 / 4 Min.      | 14.0 / 8.7<br>± 5                | lbs     | 62 / 39<br>± 22     | N       |
| Adhesion (MD)<br>FSTM191.5970          | 6 Min.          | 12.0 ± 4                         | lbs     | 53.4 ± 18           | N       |
| Standard Width                         |                 | 54 or 38                         | inches  | 1372 or 965         | mm      |
| Abrasion (Tabor)<br>FSTM191.5306       | No Wear         | No Wear (CS17 Wheel, 500 Cycles) |         |                     |         |
| Corrosion<br>Section 4.5.5             | Pass            | No Evidence of Corrosion         |         |                     |         |
| Permeance<br>FSTM191.5516              | No Leakage      | No Leakage                       |         |                     |         |
| Blocking<br>FSTM191.5872               | #3 Max.         | #1 Rating                        |         |                     |         |

<sup>\*</sup>The information contained in this technical data bulletin is believed to be true and accurate. The typical physical properties are from historical testing and should not be considered a specification. This information is to be used only as a guide. It is the responsibility of the end user to determine the suitability of our products for each specific application.

