

DURAPRO[®] 6022

Description: **DURAPRO[®] 6022** is a vinyl laminated, reinforced industrial fabric engineered to give longer life to tent tops and awnings. DURAPRO[®] 6022 utilizes, UV stabilizers, outdoor pigment systems, mildew inhibitors, low temperature plasticizers and flame-retardant additives

Applications: All-weather General Purposes

Available Colors: White, Yellow, Red, Green and Blue

TYPICAL PHYSICAL PROPERTIES

Test and Methods	Imperial		Metric	
	Result	Unit	Result	Unit
Weight FSTM191.5041	16.3 ± 1	oz/yd ²	0.55 ± 0.034	kg/m ²
Adhesion (Face/Back) ASTM D751	6 / 7 ± 1	lbs/inch	26.7 / 31.1 ± 4.4	N/25mm
Vertical Flammability (MD/CD) FSTM191.5903	---	---	---	---
After Flame	5.3 / 6.9 ± 1.0	seconds	5.3 / 6.9 ± 1.0	seconds
Char Length	4.9 / 5.1 ± 1.0	inches	124.5 / 129.5 ± 25.4	mm
Hydrostatic Mullen FSTM191.5512	393 ± 20	PSI	2709.6 ± 137.9	kPa
Tear –Tongue (MD/CD) FSTM191.5134	41 / 42 ± 10	lbs	182.4 / 186.8 ± 44.5	N
Tensile Strength-Grab (MD/CD) FSTM191.5100	230 / 200 ± 10	lbs	1023.1 / 889.6 ± 44.5	N
Standard Width	61	inches	1549.4	mm
Standard Length	50	yards	45.72	m

The information contained in this technical data bulletin is believed to be true and accurate. The typical physical properties are from historical testing and should not be considered a specification. This information is to be used only as a guide. It is the responsibility of the end user to determine the suitability of our products for each specific application.

03.01.17 JB