

## **DURASONIC® 5004**

Description: DURASONIC® 5004 is a 0.21 lb/ft<sup>2</sup> reinforced mass-loaded vinyl barrier. DURASONIC® is a field proven family of noise-abatement products characterized by high weight to volume (mass) flexible vinyl structure and meets the requirements of BMS8-47F Type 3.

Available Colors: Gray.

Test and Methods	Imperial			<u>Metric</u>	
	Spec.	*Typical	Unit	*Typical	Unit
Weight FSTM191.5041	30 ± 2	30 ± 1	oz/yd <sup>2</sup>	1.02 ± 0.034	kg/m <sup>2</sup>
Thickness FSTM191.5030	0.024 Max.	0.020 ± 0.002	inches	0.51 ± 0.051	mm
Adhesion ASTM D751	3.0 Min.	10.0 ± 1.0	lbs/inch	44.48 ± 4.4	N/25mm
Vertical Flame (MD/CD) FAR 25.853(a)(1)(ii)					
After Flame	< 15	0.5 / 0.5	seconds	0.5 / 0.5	seconds
Burn Length	< 8	2.3 / 2.5	inches	58.4 / 63.5	mm
Drip Time	< 5	0.0 / 0.0	seconds	0.0 / 0.0	seconds
Tensile – Grab (MD/CD) FSTM191.5100	110 Min.	330 / 330 ± 50	lbs	1467.9 / 1467.9 ± 222.4	N
Tear – Trapezoid (MD/CD) ASTM D1117	12 Min.	25 / 20 ± 5	lbs	111.2 / 89.0 ± 22.2	N
High Temperature Resistance Section 8.5	Pass	Pass	Pass/Fail	Pass	Pass/Fail
Corrosion Section 8.3	Pass	Pass	Pass/Fail	Pass	Pass/Fail
Standard Width		48	inches	1219.2	mm

## PHYSICAL PROPERTIES

\*The information contained in this technical data bulletin is believed to be true and accurate. The typical physical properties are from historical testing and should not be considered a specification. This information is to be used only as a guide. It is the responsibility of the end user to determine the suitability of our products for each specific application.

03.01.17 JB

go beyond.

## MATERIAL SOLUTIONS THAT REDEFINE PERFORMANCE

350 NORTH DIAMOND ST. • RAVENNA, OH 44266 • USA • www.duracote.com Toll-Free: 800.321.2252 • USA: +1.330.296.9600 • Fax: 330.296.5102