

## DURAPRO<sup>®</sup> 6116

- Description:** DURAPRO<sup>®</sup> 6116 is a vinyl laminated, reinforced industrial fabric with a Light Taffeta or Leatherette emboss.
- Applications:** Tarpaulins, Windbreakers, Protective Curtains, Covers, Gym Mats and All-weather General Purposes
- Available Colors:** 4022 White, 4490 Blue, 3115 Yellow, 9800 Black, 3902 Gray, 4335 Red, 5459 Navy, 4344 Burgundy, 4539 Green
- Compliance:** Registered as Flame Resistant by the California Fire Marshal (F-67101)

### TYPICAL PHYSICAL PROPERTIES

Test and Methods	Imperial		Metric	
	Result	Unit	Result	Unit
<b>Weight</b> FSTM191.5041	17 ± 1	oz/yd <sup>2</sup>	0.58 ± 0.034	kg/m <sup>2</sup>
<b>Adhesion (Face/Back)</b> ASTM D751	10 / 10 ± 1	lbs./inch	44.5 / 44.5 ± 4.4	N/25mm
<b>Vertical Flammability (MD/CD)</b> FSTM191.5903	---	---	---	---
After Flame	4.9 / 4.1 ± 2	seconds	4.9 / 4.1 ± 2	seconds
Char Length	3.9 / 3.4 ± 1	inches	99.1 / 86.4 ± 25.4	mm
<b>Hydrostatic Mullen</b> FSTM191.5512	370	PSI	2551.1	kPa
<b>Tear –Tongue (MD/CD)</b> FSTM191.5134	37 / 55 ± 10	lbs.	164.6 / 244.7 ± 44.5	N
<b>Tensile Strength-Grab (MD/CD)</b> FSTM191.5100	230 / 200 ± 15	lbs.	1023.1 / 889.6 ± 66.7	N
<b>Standard Width</b>	62	inches	1574.8	mm
<b>Standard Length</b>	50	yards	45.72	m

The information contained in this technical data bulletin is believed to be true and accurate. The typical physical properties are from historical testing and should not be considered a specification. This information is to be used only as a guide. It is the responsibility of the end user to determine the suitability of our products for each specific application.

03.01.17 JB