

## Duracote DURUG<sup>®</sup> Coin Pattern Floor Covering for Aircraft

**DURUG<sup>®</sup>** is designed for use as a floor covering of new and retrofit aircraft providing an attractive, flexible, scuff-resistant floor covering. **DURUG<sup>®</sup>** delivers excellent anti-fatigue properties where people are required to stand for prolonged periods of time. Available without an underlay or a 1/8" (3.2 mm) or 1/4" (6.4 mm) closed cell, non-absorbent foam underlay.

**COMPLIANCES:** **DURUG<sup>®</sup>** is manufactured to various Lockheed (LAC) and Boeing (BMS) specifications, as well as, Federal Standard 595 (FDS) color requirements. **DURUG<sup>®</sup>** is flame resistant to FAR 25.853(a)(1)(ii).

**RESISTANT TO:** Abrasion – Static – Water – Most Oils – Chemicals – Grease – Rot – Mildew

**COLORS:** Duracote's custom color laboratory can custom-match virtually any color. Please provide a Federal Color Standard 5-digit number, Duracote color number, or a color swatch. Tri-tone is available upon request.

### TYPICAL PHYSICAL PROPERTIES\*

	FOAM AND NO FOAM UNDERLAY	
	No Foam	1/8" Foam Backing
<b>Emboss</b>	Coin	Coin
<b>Color Type</b>	Single	Single
<b>Certified to Specification</b>	FAR 25.853(a)	FAR 25.853(a)
<b>Weight</b> FSTM 191.5041	50-54.8 oz/yd <sup>2</sup> (1.69 – 1.86 kg/m <sup>2</sup> )	65.0-69.0 oz/yd <sup>2</sup> (2.20 – 2.33 kg/m <sup>2</sup> )
<b>Tabor Abrasion</b> CS10, 1000g, 650	No Wear	No Wear
<b>Vertical Flame</b> FAR 25.853(a)(1)(ii)	Pass	Pass
<b>Tear-Trap (MD / CD)</b> ASTM D1117	55.5 / 64.6 lbs (246.9 / 287.4 N)	Not Tested
<b>Surface Resistivity</b> ASTM D257	10 <sup>9</sup> – 10 <sup>12</sup> ohms (Anti-Static)	10 <sup>9</sup> – 10 <sup>12</sup> ohms (Anti-Static)

**Standard Width is 54" (1372 mm) – Minimum Order is 50 linear yards (46 linear meters) per color**

NOTE: The information provided is the best currently available and has been obtained by prevailing test methods. It is true and accurate to the best of our knowledge at this time. The information is provided as guidelines, should not be considered as specifications and is subject to revision as additional knowledge and experience on this product are gained. It is the responsibility of the end user to determine the suitability of our products for their particular application.

10/30/19 M.M.